

CONCRETOS



PIRO

PIRO INTERNACIONAL S.A DE C.V.

Concreto Aislante

	TEMP. °C MÁXIMA DE SERVICIO	MATERIA PRIMA	CANTIDAD NECESARIA COLADO kg/m³	ALUMINA PROMEDIO%	SÍLICE PROMEDIO%
Everlite 100-0, 5-5- MX (Legrit 100-0,5-5 M)	900°C	Vermiculita	550	10.0	35.0
Everlite 100-0, 8-5- MX (Legrit 100-0,8 -5 M)	1,000°C	Chamota, Vermiculita	780	22.0	36.0
Everlite 120-0.9LI 0-2 MX (Legrit 120-0,9 LI-2 MX/Legrit 110-0,7 0-4 M)	1,200°C	Arena de sílice, Perlita	950	36.0	51.0
Everlite 125-0, 9-2- MX (Legrit 125-0,9-2 M)	1,200°C	Chamota, Perlita	1,100	46.0	37.0
Everlite Cast 135-1,2AL 0-5 MX (Legrit 135-1.2AL 0-5 M)	1,350°C	Chamota, Perlita	1,200	45.0	40.0
Everlite Gun 135-1,2-2-MX (Legrit 135-1,2S 0-2-M)	1,350°C	Chamota, Perlita	1,200	45.0	40.0
Everlite Cast 135-1, 3-2- MX (Legrit 135-1,3-2 M)	1,350°C	Chamota, Perlita	1,300	48.0	37.0

Concreto
Refractario



Tel: +52 (33) 3619 3800/ 3619 6540/
3650 3557/ 3619 2592

Av. Washington 61, Col. Moderna. C.P. 44190.
Guadalajara, Jal. México.



piro.mx



PIROGL



PIRO_GDL



RHI MAGNESITA
Distribuidor Autorizado