

CONCRETOS

Concreto Bajo Cemento

		TEMP. °C MÁXIMA DE SERVICIO	MATERIA PRIMA	CANTIDAD NECESARIA COLADO kg/m³	ALUMINA PROMEDIO%	SÍLICE PROMEDIO%
Evercast LC B82AL-5-MX (Didurit B82AL-5M)	—▷	1,200°C	Bauxita	2,750	82.0	11.0
Evercast LC M66AL-5-MX (Didurit M66AL-5M)	—▷	1,300°C	Rica en mullita	2,560	65.0	28.0
Evercast LC F43AL-8-MX (Didurit F43AL-8-MX)	—▷	1,300°C	Chamota	2,230	43.0	50.0
Evercast LC F38-5-MX (Didurit F38-5M)	—▷	1,400°C	Chamota	2,200	38.0	55.0
Evercast LC F46-5-MX (Didurit F46-5 M)	—▷	1,500°C	Chamota	2,250	47.0	47.0
Evercast LC F50-6-MX (Didurit F50-6M)	—▷	1,550°C	Chamota	2,340	48.0	47.0
Evercast LC B83S-8-MX (Didurit B83S-8M)	—▷	1,650°C	Bauxita	2,740	83.4	11.6
Evercast LC M66-5-MX (Didurit M66-5M)	—▷	1,680°C	Bauxita	2,480	66.0	28.0
Evercast LC B83-8-MX (Didurit B83-8M)	—▷	1,700°C	Bauxita	2,760	82.0	12.5
Evercast LC M67-8-MX (Didurit M67-8-M)	—▷	1,760°C	Rica en mullita	2,450	67.5	29.0
Evercast LC M67S-8-MX (Didurit M67S-8-M)	—▷	1,760°C	Rica en mullita	2,450	67.5	29.0
Evercast LC A94CR-6-MX (Didurit A94CR-6-M/Didurit A94CR-6-M)	—▷	1,800°C	Alumina sinterizada, Óxido de cromo	3,000	94.0	0.1
Evercast LC A92MAM-15-MX (Didurit A92MA-6-M)	—▷	1,800°C	Alumina sinterizada MA-espinales	3,050	92.0	0.2
Evercast LC A96M-6-MX (Didurit A96M-6-M)	—▷	1,870°C	Alumina sinterizada	2,950	96.0	0.1

Tel: +52 (33) 3619 3800/ 3619 6540/
3650 3557/ 3619 2592

Av. Washington 61, Col. Moderna. C.P. 44190.
Guadalajara, Jal. México.

 piro.mx  PIROGL  PIRO_GDL

Concreto
Refractario

