

# LADRILLOS

## Densos

|                  |                 |         | DENSIDAD<br>PROMEDIO | POROSIDAD<br>APARENTE | ALUMINA<br>PROMEDIO% | SÍLICE<br>PROMEDIO% |
|------------------|-----------------|---------|----------------------|-----------------------|----------------------|---------------------|
| ALTA CALIDAD     | MAXIAL 36-IN    | 1,250°C | 2.20                 | 19.5                  | 55.0                 | 40.0                |
|                  | MAXIAL 20-IN    | 1,280°C | 2.10                 | 18.0                  | 29.0                 | 63.0                |
|                  | MAXIAL 210-M    | 1,400°C | 2.28                 | 18.0                  | 44.0                 | 51.0                |
|                  | MAXIAL 215-M    | 1,400°C | 2.26                 | 18.0                  | 45.0                 | 50.0                |
| CALIDAD SUPERIOR | MAXIAL 42-M     | 1,400°C | 2.28                 | 18.0                  | 44.0                 | 51.0                |
|                  | MAXIAL 300C-M   | 1,400°C | 2.38                 | 15.0                  | 50.0                 | 43.0                |
|                  | MAXIAL 334-M    | 1,500°C | 2.25                 | 14.0                  | 35.0                 | 60.0                |
|                  | MAXIAL 310-M    | 1,500°C | 2.32                 | 14.0                  | 44.0                 | 52.0                |
|                  | MAXIAL 300-M    | 1,500°C | 2.29                 | 17.0                  | 45.0                 | 50.0                |
| ALTA ALUMINA     | RESISTAL B70-M  | 1,400°C | 2.58                 | 19.0                  | 73.0                 | 22.0                |
|                  | RESISTAL M60-M  | 1,500°C | 2.45                 | 17.0                  | 60.0                 | 35.0                |
|                  | RESISTAL B75-M  | 1,500°C | 2.65                 | 20.0                  | 77.0                 | 18.0                |
|                  | RESISTAL B50-M  | 1,500°C | 2.40                 | 20.0                  | 58.5                 | 36.5                |
|                  | RESISTAL M50-M  | 1,600°C | 2.43                 | 16.0                  | 54.4                 | 41.5                |
|                  | RESISTAL M50C-M | 1,600°C | 2.45                 | 14.7                  | 55.0                 | 39.7                |
|                  | RESISTAL B65-M  | 1,600°C | 2.54                 | 20.0                  | 68.0                 | 26.0                |
|                  | RESISTAL M70-M  | 1,600°C | 2.50                 | 17.0                  | 68.0                 | 28.0                |
|                  | RESISTAL M70C-M | 1,600°C | 2.67                 | 15.0                  | 69.0                 | 24.7                |
|                  | RESISTAL B80-M  | 1,600°C | 2.75                 | 20.0                  | 80.0                 | 15.5                |

Tel: +52 (33) 3619 3800/ 3619 6540/  
3650 3557/ 3619 2592

Av. Washington 61, Col. Moderna. C.P. 44190.  
Guadalajara, Jal. México.

# LADRILLOS



# PIRO

PIRO INTERNACIONAL S.A DE C.V.

## Densos

EXTRA ALTA ALUMINA

RESISTAL B85C M 1,550°C

RESISTAL B80C M 1,600°C

RESISTAL B85AC M 1,600°C

RESISTAL A90C M 1,600°C

RESISTAL A90M 1,600°C

RESISTAL A95C M 1,600°C

| DENSIDAD<br>PROMEDIO | POROSIDAD<br>APARENTE | ALUMINA<br>PROMEDIO% | SÍLICE<br>PROMEDIO% |
|----------------------|-----------------------|----------------------|---------------------|
| 2.82                 | 15.0                  | 81.0                 | 13.0                |
| 2.84                 | 15.0                  | 80.0                 | 12.5                |
| 2.84                 | 15.0                  | 80.0                 | 13.0                |
| 2.93                 | 13.1                  | 85.8                 | 9.0                 |
| 2.96                 | 17.2                  | 91.2                 | 7.8                 |
| 3.05                 | 12.5                  | 92.0                 | 5.5                 |

Tel: +52 (33) 3619 3800/ 3619 6540/  
3650 3557/ 3619 2592

Av. Washington 61, Col. Moderna. C.P. 44190.  
Guadalajara, Jal. México.

