

CONCRETOS



PIRO

PIRO INTERNACIONAL S.A DE C.V.

Concreto Libre de Agua

	TEMP. °C MÁXIMA DE SERVICIO	MATERIA PRIMA	CANTIDAD NECESARIA COLADO kg/m³	ALUMINA PROMEDIO%	SÍLICE PROMEDIO%
Evergun Sol F53-6-MX (Compac Sol F53-6M)	1,600°C	Chamota	2,400	53.0	44.0
Evercast Sol M64-5-MX (Compac Sol M64-5M)	1,700°C	Rica en mullita	2,470	64.0	31.0
Evercast Sol B88-6-MX (Compac Sol B88-6M)	1,700°C	Buaxita	2,850	87.5	8.1
Evershot LC M67-8-MX (Compac Shot B83-8-M/Compac Shot F48-8-M/ Compac Shot M67-8-M)	1,704°C	Alumina calcinada Cemento aluminoso, Chamota mullítica	2,500	67.5	28.1
Evercast Sol A97-15-MX (Compac Sol A97-15-M)	1,750°C	Alumina sinterizada	3,050	96.0	3.0
Evercast Sol A87CR-6-MX (Compac Sol A87CR-6-M/ Compac Sol A94CR-6-M)	1,800°C	Alumina sinterizada, Óxido de cromo	3,000	87.0	2.0
Evercast Sol MB A100-15-MX (Compac Sol MB A100-15M)	1,850°C	Alumina sinterizada	3,100	98.5	1.0
Evercast Sol MB A100-6-MX (Compac Sol MB A100-6-M)	1,850°C	Alumina sinterizada	3,100	98.5	1.0

Concreto
Refractario



Tel: +52 (33) 3619 3800/ 3619 6540/
3650 3557/ 3619 2592

Av. Washington 61, Col. Moderna. C.P. 44190.
Guadalajara, Jal. México.



piro.mx



PIROGL



PIRO_GDL



RHI MAGNESITA
Distribuidor Autorizado