

LADRILLOS



PIRO

PIRO INTERNACIONAL S.A DE C.V.

Aislantes

			DENSIDAD PROMEDIO	POROSIDAD APARENTE	ALUMINA PROMEDIO%	SÍLICE PROMEDIO%
QUEMADO	LEGRAL 05/12	1,095°C	1.10	N/A	40.0	50.0
	LEGRAL 25/09	1,260°C	0.90	N/A	38.0	44.0
	LEGRAL 40/08	1,425°C	1.12	N/A	56.0	39.0
	LEGRAL 50/10	1,535°C	1.10	N/A	56.0	39.0
NO QUEMADO	LEGRAL 05/07	1,095°C	0.65	N/A	9.5	65.5
	LEGRAL 25/08	1,260°C	0.85	N/A	36.0	44.0

Tel: +52 (33) 3619 3800/ 3619 6540/
3650 3557/ 3619 2592

Av. Washington 61, Col. Moderna. C.P. 44190.
Guadalajara, Jal. México.



piro.mx PIROGL PIRO_GDL